



## Future Coat Technology

### **FCT BARREL NI 201 SERIES**

The high leveled, ductile and mirror bright decorative FCT BARREL NI 201 B is used for rack plating applications on complicated parts or when the article is bent afterwards.

#### **Make up data**

	Optimum	Range
NiSO <sub>4</sub> *6H <sub>2</sub> O	270gm/Ltr	250-290gm/Ltr
NiCl <sub>2</sub> *6H <sub>2</sub> O	60gm/Ltr	50-70gm/Ltr
H <sub>3</sub> BO <sub>3</sub>	45gm/Ltr	40-50gm/Ltr
FCT BARREL NI 201 A	10ml/Ltr	5-20ml/Ltr
FCT BARREL NI 201 B	0.8ml/Ltr	0.4-1ml/Ltr

#### **Make up procedure**

1. In to a separate and clean tank, hot water is filled up to approximately 60% tank volume.
2. While stirring, add slowly and carefully the required quantity of Nickel chloride in to the water.
3. While continue stirring, add slowly and carefully the required quantity of boric acid into the water.
4. While further stirring , add slowly and in small quantities the required quantity of Nickel sulphate into the water.
5. Add 3g/l activated carbon powder into the solution and stir for at least 30 minuts , then stop all agitation and allow carbon to settle down.
6. Filter the solution through a 5 micrometer mesh filter media into the working tank. Make sure no active carbon particles are in the working solution.
7. Top working tank with water up to operation level and switch on air agitation.
8. Measure and adjust the pH with diluted (1:10) sulphuric acid to operation range.
9. Add the necessary quantity of additives.
10. Switch on circulation filter pump.
11. Adjust operation temperature if necessary to operation range.

12. Dummy plate for approximately 2 ampere hours per litre.

13. Solution is ready for start up.

### **Operation Conditions**

Agitation	Necessary,  Preferably air, mechanical also possible
Filtration	Continuous, 5-8 tank volumes per hour throughput, 5-10  Micrometer mesh filter media.
Cathodic Current Density	Up to 8A/dm <sup>2</sup>
Temperature	55 <sup>0</sup> C-65 <sup>0</sup> C
Anodes	Bagged Nickel anode pieces in Titanium baskets
Plating speed	1micron/minute at 5A/dm <sup>2</sup>
Tank ventilation	Necessary

### **Maintenance**

Under standard production conditions dosing of the FCT BARREL NI 201 A and the FCT BARREL NI 201 B to the electrolyte is done according to ampere hours. In case ampere hours are not known, additions of FCT BARREL NI 201 B should not exceed 0.2ml/Ltr.At once. It is recommended to make corrective additions in small doses. Dosing ratio of FCT BARREL NI 201 B to FCT BARREL NI 201 A is approximately 1:1.

### **Consumption per 1000 Ampere**

FCT BARREL NI 201 A	150-200ml
FCT BARREL NI 201B	100-150ml

### **Trouble shooting**

- Poor LCD performance is caused by lack of FCT BARREL NI 201 A or by excess of FCT BARREL NI 201 B or by third party Nickel additives and residues. Add 2ml/Ltr FCT BARREL NI 201 A to correct and stop dosing of FCT BARREL NI 201 B for a while.
- Orange skin formation at high and mid current densities indicates excessive FCT BARREL NI 201 B or is caused by foreign additives.
- Permanent loss of compressive stress is caused by foreign additives and indicates the need for carbon treatment.

**Effluent treatment**

All concentrates and rinsing waters have to be treated according to local regulations.

“The above information is given in good faith and is based on our experience but no condition of warranty is to be implied”